

DECLARATION OF PERFORMANCE No 09/2025

1. Unique identification code of the product-type: **C E L S A H**

Product name:
Round bars $\phi 10 \div \phi 102$
Flat bars width $12 \times 4 \div 250 \times 30$
Square bars $10 \times 10 \div 20 \times 20$
Angles $20 \times 20 \times 3 \div 150 \times 150 \times 15$
Channels UPN $80 \div 300$
Normal flange I-beams IPN $80 \div 300$
Economical parallel flange I-beams IPE $80 \div 300$
Wide flange I-beams HEA $100 \div 180$
Wide flange I-beams HEB $100 \div 180$
Steel grade: S235, S275, S355 in qualities: JR, J0, J2

Flat bars width 300×30
Steel grade: S235, S275, in qualities: JR, J0, J2

2. Intended use/es:

Metal structures or in composite metal and concrete structures

3. Manufacturer:

**CELSA „Huta Ostrowiec” Sp. z o.o.,
ul. Samsonowicza 2,
27-400 Ostrowiec Św.,
tel. +48 41 249 30 00, fax. +48 41 249 22 22, celsaho@celsaho.com**

5. System/s of AVCP: **2+**

6. Harmonised standard: **EN 10025-1:2004**

Notified body/es:

**Ośrodek Badań i Certyfikacji
SIMPTTESTCERT Sp. z o.o.,
Zakład Certyfikacji
40-615 KATOWICE,
ul. Gen. Zygmunta Waltera Jankego 11
Number: 1458**

7. Declared performance

Essential characteristics	Declared performance				Harmonised technical specification
Tolerances on dimensions and shape	pass				EN 10025-1:2004
Elongation	Nominal thickness [mm]	≥ 3 ≤ 40	> 40 ≤ 63	> 63 ≤ 100	EN 10025-1:2004
	Minimum percentage elongation after fracture [%]				
	S235JR, S235J0	26	25	24	
	S235J2	24	23	22	
	S275JR, S275J0	23	22	21	
	S275J2	21	20	19	
	S355JR, S355J0, S355J2	22	21	20	
Tensile strenght	S235JR, S235J0, S235J2	Rm = 360 + 510 MPa			EN 10025-1:2004
	S275JR, S275J0, S275J2	Rm = 410 + 560 MPa			
	S355JR, S355J0, S355J2	Rm = 470 + 630 MPa			

Essential characteristics	Declared performance												Harmonised technical specification	
Yield strenght	Nominal thickness [mm]	≤ 16			> 16 ≤ 40		> 40 ≤ 63		> 63 ≤ 80		> 80 ≤ 100		EN 10025-1:2004	
	Minimum yield strenght R _{ext} [MPa]													
	S235JR, S235J0, S235J2	235			225		215		215		215			
	S275JR, S275J0, S275J2	275			265		255		245		235			
	S355JR, S355J0, S355J2	355			345		335		325		315			
Impact strenght	S235JR, S275JR, S355JR	Min average energy in temperature 20°C 'not applicable or ≥ 27 J												EN 10025-1:2004
	S235J0, S275J0, S355J0	Minimum average energy in temperature 0°C ≥ 27 J												
	S235J2, S275J2, S355J2	Minimum average energy in temperature -20°C ≥ 27 J												
Weldability (Chemical composition) Durability (Chemical composition) * Values for analysis from the product		C			Si	Mn	P	S	Cu	N	CEV			EN 10025-1:2004
	Nominal thickness [mm]	≤ 16	> 16 ≤ 40	> 40							≤ 30	> 30 ≤ 40	> 40	
	max. [%]													
	S235JR	0,19	0,19	0,23	-	1,40	0,045	0,045	0,55	0,014	0,35	0,35	0,38	
	S235J0	0,19	0,19	0,19	-	1,40	0,040	0,040	0,55	0,014	0,35	0,35	0,38	
	S235J2	0,19	0,19	0,19	-	1,40	0,035	0,035	0,55	-	0,35	0,35	0,38	
	S275JR	0,24	0,24	0,25	-	1,50	0,045	0,045	0,55	0,014	0,40	0,40	0,42	
	S275J0	0,21	0,21	0,21	-	1,50	0,040	0,040	0,55	0,014	0,40	0,40	0,42	
	S275J2	0,21	0,21	0,21	-	1,50	0,035	0,035	0,55	-	0,40	0,40	0,42	
	S355JR	0,27	0,27	0,27	0,55	1,60	0,045	0,045	0,55	0,014	0,45	0,47	0,47	
	S355J0	0,23	0,23	0,24	0,55	1,60	0,040	0,040	0,55	0,014	0,45	0,47	0,47	
	S355J2	0,23	0,23	0,24	0,55	1,60	0,035	0,035	0,55	-	0,45	0,47	0,47	

The performance of the product identified above is in conformity with the set of declared performance. This declaration of performance is issued in accordance with Regulation (UE) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Robert Martynowski

at Ostrowiec Świętokrzyski



Robert Martynowski

Dyrektor Jakości
Celsa Huta Ostrowiec

on 2025-10-20

This declaration replaces:

Declaration of Performance No 01/2025 dated 2025-06-13 r.
Declaration of Performance No 03/2024 dated 2024-03-27 r.
Declaration of Performance No 01/2023 dated 2023-05-23 r.
Declaration of Performance No 06/2020 dated 20.05.2020 r.
Declaration of Performance No 06/2020 dated 20.05.2020 r.
Declaration of Performance No 02/2019 dated 19.06.2019 r.
Declaration of Performance No 04/2017 dated 31.03.2017 r.
Declaration of Performance No 03/2016 dated 10.10.2016 r.
Declaration of Performance No 02/2016 dated 04.07.2016 r.
Declaration of Performance No 01/2016 dated 23.05.2016 r.
Declaration of Performance No 01/2013 dated 01.07.2013 r.